

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 211 563 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.06.2002 Bulletin 2002/23

(51) Int Cl.7: **G03F 7/42**, H01L 21/3213,
C11D 7/26, C11D 7/32,
C11D 3/39, C11D 7/50,
C11D 11/00

(21) Application number: **01128335.5**

(22) Date of filing: **29.11.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **30.11.2000 JP 2000369625**
27.12.2000 JP 2000399153
27.12.2000 JP 2000399154
13.03.2001 JP 2001070360
20.04.2001 JP 2001123252

(71) Applicant: **Tosoh Corporation**
Shinnanyo-shi, Yamaguchi-ken, 746-8501 (JP)

(72) Inventors:
• **Hara, Yasushi**
Shinnanyo-shi, Yamaguchi-ken (JP)
• **Aoki, Masahiro**
Shinnanyo-shi, Yamaguchi-ken (JP)
• **Hayashi, Hiroaki**
Hikari-shi, Yamaguchi-ken (JP)

(74) Representative: **VOSSIUS & PARTNER**
Siebertstrasse 4
81675 München (DE)

(54) **Resist stripper**

(57) A resist stripper which comprises a peroxide and a quaternary ammonium salt.

EP 1 211 563 A1

Description

[0001] The present invention relates to a stripper to strip a photoresist layer and a titanium oxide in production process of e.g. semiconductor integrated circuits, printed wiring boards and liquid crystals.

[0002] A semiconductor integrated circuit is produced by such a method that a photoresist is coated on a substrate, followed by exposure and development, then etching is carried out to form a circuit, and then the photoresist is stripped from the substrate, or ashing is carried out after formation of the circuit, the resist is removed, and then the remaining resist residue is stripped. To strip the photoresist from the substrate, or to strip the resist residue from the substrate, various resist strippers have conventionally been proposed.

[0003] For example, JP-A-62-49355 discloses a resist stripping liquid composition employing an alkanolamine. However, the stripping liquid composition employing an alkanolamine is insufficient for stripping of a resist residue degenerated to have inorganic properties by a treatment such as dry etching, ashing or ion implantation. Further, in a latest submicron treatment technique, a metal material containing e.g. TiN or TiSi is used, but in a case of using such a metal material, a stable by-product such as a titanium oxide tends to form during the treatment. A titanium oxide could not be stripped with a conventionally used alkanolamine.

[0004] Accordingly, as a resist stripping liquid composition having more excellent stripping properties, one containing hydroxylamine has been proposed in recent years. For example, JP-A-4-289866 proposes a resist stripping liquid composition containing hydroxylamine and an alkanolamine, and JP-A-6-266119 proposes a resist stripping liquid composition containing hydroxylamine, an alkanolamine and catechol. Although this resist stripping composition containing hydroxylamine provides excellent titanium oxide stripping properties, it is an unstable compound, and accordingly there is a risk of e.g. decomposition or explosion.

[0005] In addition to the above amine type resist stripper showing basicity, a resist stripper by a combination of hydrogen peroxide and an acid has also been proposed (e.g. JP-A-64-15740). A titanium oxide is generally known to dissolve in hydrogen peroxide in an acidic condition, however, combination of hydrogen peroxide and an acid is not optimal for stripping of an alkali development type photoresist which is likely to be stripped in a basic condition.

[0006] As described above, conventionally proposed resist strippers have insufficient stripping properties, particularly stripping properties of a titanium oxide, and with which there is a risk of decomposition or explosion. Accordingly, it is an object of the present invention to provide a resist stripper containing no hydroxylamine having a high risk of explosion and providing excellent resist stripping properties and titanium oxide stripping properties.

[0007] This object could be achieved on the basis of the finding that a resist stripper comprising a peroxide and a quaternary ammonium salt is useful as a resist stripper having excellent resist stripping properties and titanium oxide stripping properties.

[0008] Namely, the present invention resides in a resist stripper comprising a peroxide and a quaternary ammonium salt.

[0009] Now, the present invention will be described in detail with reference to the preferred embodiments.

[0010] In the present invention, stripping is to remove a resist or a resist residue remaining after formation of a circuit, obtained by coating a photoresist on a substrate, followed by exposure and development, then carrying out a treatment such as etching. Namely, development is removal of a resist solubilized in liquid by exposure of a photoresist, and stripping is removal of a portion remaining after the development or a portion which becomes hardly soluble in liquid by means of a treatment such as etching or ashing.

[0011] The resist stripper of the present invention is useful to strip a photoresist or its residue. Namely, a photoresist is coated on a substrate, followed by exposure and development, and then a treatment such as etching is carried out to form a circuit, and then the photoresist is stripped by the stripper of the present invention. Otherwise, after formation of the circuit, ashing is carried out to remove the resist, and then the remaining resist residue is stripped by the stripper of the present invention.

[0012] The resist stripper of the present invention strips a titanium oxide which is a by-product in formation of a circuit, as well as the resist. A titanium oxide, particularly a tetravalent titanium oxide is an extremely stable compound and is hardly soluble in water. As the titanium oxide, one having various valency such as tetravalent, trivalent or bivalent may be mentioned, and it is the tetravalent titanium oxide (titanium dioxide) that is most insoluble. On the other hand, a most soluble titanium species is Ti^{2+} , and a solid phase titanium oxide is known to easily be dissolved by reduction in an acidic region. However, the resist stripper of the present invention reduces and dissolves, and strips various titanium oxides including titanium dioxide which is most insoluble in an alkaline region at which the resist can be stripped.

[0013] Essential components of the resist stripper of the present invention are a peroxide and a quaternary ammonium salt.

[0014] The peroxide to be used in the resist stripper of the present invention acts as a reducing agent.

[0015] The peroxide to be used in the resist stripper of the present invention is at least one member selected from hydrogen peroxide, a persulfate, a perborate, a percarbonate, an organic peracid and an organic hydroperoxide. Among them, hydrogen peroxide is industrially preferred since it is available at a lowest cost.

[0016] Hydrogen peroxide may be used as an anhydride or an aqueous solution, or as a peroxyhydrate of e.g. urea or a quaternary ammonium salt (one having hydrogen peroxide coordinated to urea or a quaternary ammonium salt, such as water in water of crystallization).

[0017] The inorganic per salt such as persulfate, perborate or percarbonate is used preferably as a salt with ammonia or an amine or as a quaternary ammonium salt. Other salts such as sodium salt or potassium salt may be used, however, removal of metal ions is required, such being unfavorable industrially.

[0018] The organic peracid is not particularly limited so long as it is stable when mixed with a quaternary ammonium salt, and it may, for example, be performic acid, peracetic acid, benzoyl peroxide or m-chloroperbenzoic acid.

[0019] The organic hydroperoxide is a compound represented by a general formula R-OOH (wherein R is an alkyl or aryl) and examples of which include butyl hydroperoxide and cumyl hydroperoxide.

[0020] The quaternary ammonium salt to be used for the resist stripper of the present invention may be any one showing alkalinity. Examples of the quaternary ammonium salt include quaternary ammonium hydroxide, a quaternary ammonium carbonate, a quaternary ammonium carboxylate and a quaternary ammonium peroxy-carboxylate. They are all alkaline substances and they may be used alone or as a mixture. Among these quaternary ammonium salts, particularly preferred is hydroxide or a carboxylate. As a carboxylic acid, either aliphatic carboxylic acid or aromatic carboxylic acid may be used, but an aromatic carboxylic acid is preferred industrially since it has a good stability. The aromatic carboxylic acid may, for example, be benzoic acid, salicylic acid or phthalic acid. The aliphatic carboxylic acid may, for example, be acetic acid, lactic acid, adipic acid or propionic acid.

[0021] The cation moiety in the quaternary ammonium salt to be used for the resist stripper of the present invention, i.e. the quaternary ammonium, may be a tetraalkylammonium such as tetramethylammonium, tetraethylammonium, tetra n-propylammonium, triethylmethylammonium or dodecyltrimethylammonium, a benzyl trialkylammonium such as benzyl trimethylammonium, or an alkyl-hydroxyalkylammonium such as trimethyl-2-hydroxyethylammonium (choline).

[0022] To the resist stripper of the present invention, in addition to the peroxide and the quaternary ammonium salt, at least one member selected from an amine, a water soluble organic solvent and water may be added. As an amine to be added to the resist stripper, an amine which is conventionally used as a resist stripper may be added. Specific examples of an amine include alkanolamines such as monoethanolamine, diethanolamine, triethanolamine, 2-(2-aminoethoxy)ethanol, N-(2-aminoethyl)ethanolamine, N,N-dimethylethanolamine, N,N-diethylethanolamine, N,N-di-*n*-butylethanolamine, N-methylethanolamine, N-ethylethanolamine, N-butylethanolamine, N-methyldiethanolamine, N-ethyldiethanolamine, monoisopropanolamine, diisopropanolamine, triisopropanolamine, N-(2-hydroxyethyl)piperazine and N-(2-hydroxyethyl)morpholine, ethyleneamines such as ethylenediamine, diethylenetriamine, triethylenetetramine, tetraethylenepentamine, pentaethylenhexamine, piperazine, N-(2-aminoethyl)piperazine and triethylenediamine, N-alkylethylenamines such as N,N,N',N'-tetramethylethylenediamine, N,N,N',N"-pentamethyldiethylenetriamine, N-methylpiperazine and N,N,N'-trimethylaminoethylpiperazine, diamines other than ethyleneamine, such as propanediamine, butanediamine and hexamethylenediamine, imidazoles such as imidazole, 1-methylimidazole, 2-methylimidazole, 1,2-dimethylimidazole, 1,2,4,5-tetramethylimidazole and 2-ethyl-4-methylimidazole, monoamines such as morpholine, cyclohexylamine, 2-ethyl-hexylamine, benzylamine and aniline, and alkylamines such as triethylamine, tripropylamine and tributylamine. Further, a hydroxylamine may be added although it is not preferred in view of corrosion or risk. These amines may be used alone or in combination as a mixture of at least two.

[0023] The water soluble organic solvent to be used in the present invention may be one which is conventionally used as a resist stripper. Examples of the water soluble organic solvent include sulfoxides such as dimethylsulfoxide, sulfones such as dimethylsulfone and diethylsulfone, amides such as N,N-dimethylformamide, N,N-diethylformamide, N,N-dimethylacetamide and N,N-diethylacetamide, lactams such as N-methyl-2-pyrrolidone, N-ethyl-2-pyrrolidone, N-propyl-2-pyrrolidone and N-hydroxyethyl-2-pyrrolidone, imidazolidinones such as 1,3-dimethyl-2-imidazolidinone, glycols such as ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, dipropylene glycol and tripropylene glycol, and glycol ethers such as ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol monobutyl ether, diethylene glycol monomethyl ether, diethylene glycol monoethyl ether, diethylene glycol monobutyl ether, propylene glycol monomethyl ether, propylene glycol monoethyl ether, propylene glycol monobutyl ether, dipropylene glycol monomethyl ether, dipropylene glycol monoethyl ether and dipropylene glycol monobutyl ether. These water soluble organic solvents may be used alone or in combination as a mixture of at least two.

[0024] To the resist stripper of the present invention, a conventionally used anticorrosive may be added. The anticorrosive may, for example, be a carboxylic acid such as formic acid, acetic acid, propionic acid, octylic acid, adipic acid, pimelic acid, sebacic acid, suberic acid, azelaic acid, benzoic acid, salicylic acid or phthalic acid, an aminopoly-carboxylic acid such as nitrilo triacetic acid, ethylenediaminetetraacetic acid or diethylenetriaminepentaacetic acid, an aromatic hydroxyl group-containing compound such as phenol, resorcinol, pyrocatechol or pyrogallol, an azole such as pyrrole, imidazole, triazole or tetrazole, or a sugar such as glucose, sucrose or fructose.

[0025] In the resist stripper of the present invention, proportions of the peroxide, the quaternary ammonium salt, water, the amine and the water soluble organic solvent vary depending upon the compounds to be used and thereby be hardly limited. However, the hydrogen peroxide is from 0.1 to 30 wt%, the quaternary ammonium salt is from 1 to

50 wt%, water is from 1 to 90 wt%, the amine is from 1 to 50 wt% and the water soluble organic solvent is from 1 to 50 wt%. Preferably, the hydrogen peroxide is from 0.5 to 25 wt%, the quaternary ammonium salt is from 5 to 50 wt%, water is from 1 to 90 wt%, the amine is from 1 to 40 wt% and the water soluble organic solvent is from 1 to 50 wt%. More preferably, the peroxide is from 1 to 25 wt%, the quaternary ammonium salt is from 5 to 40 wt%, water is from 1 to 90 wt%, the amine is from 1 to 30 wt% and the water soluble organic solvent is from 1 to 50 wt%. These compounds may be used beyond the above ranges, but the stripping properties of the resist and stability tend to decrease.

[0026] The resist stripper of the present invention may be used by adding each component when the resist is stripped, or the components may be preliminarily mixed.

[0027] The quaternary ammonium salt and the peroxide to be used for the resist stripper of the present invention may be present in a form of a mere mixture or in a form of one having the peroxide coordinated to the quaternary ammonium salt, such as a peroxyhydrate of a quaternary ammonium salt.

[0028] The peroxyhydrate having hydrogen peroxide coordinated to a quaternary ammonium salt, such as water in water of crystallization, is a stable compound, and it is possible to isolate it in the form of crystals in the air at room temperature. As a method to produce the peroxyhydrate of a quaternary ammonium salt, a conventional method for producing a peroxyhydrate can be employed, and the method is not particularly limited. A method of adding hydrogen peroxide in an equivalent amount or more to an aqueous solution of a quaternary ammonium salt, followed by heating to decompose excess hydrogen peroxide, a method of similarly adding hydrogen peroxide in an equivalent amount or more to an aqueous solution of a quaternary ammonium salt, then adding e.g. an enzyme, a metal salt or a metal thereto to decompose excess hydrogen peroxide, or a method of gradually adding hydrogen peroxide in an equivalent amount or less to a quaternary ammonium salt, may, for example, be mentioned. Further, it is allowed to use a solvent other than water for production. When hydrogen peroxide is coordinated to the quaternary ammonium salt to form a peroxyhydrate, even when the peroxyhydrate is mixed with an organic substance such as an amine which is easily oxidized with hydrogen peroxide, it does not react with the peroxyhydrate and is stable, and handling tends to be easy. Namely, when a peroxide is coordinated to a quaternary ammonium salt, in a case where another component is added to the resist stripper of the present invention, reaction of the peroxide with the additive and the reaction of the quaternary ammonium salt with the additive are suppressed, whereby wider ranges of substances can be used as an additive.

[0029] The resist stripper of the present invention can be utilized for a resist which can be developed with an aqueous alkali solution.

[0030] The resist stripper of the present invention is useful to strip a photoresist membrane coated on an inorganic substrate, a photoresist layer remaining after dry etching of a photoresist membrane coated on an inorganic substrate, or a photoresist residue remaining after ashing is carried out after dry etching, and to strip by-products such as titanium oxide. At the time of its use, stripping may be accelerated by heating or ultrasonic waves.

[0031] The resist stripper of the present invention is used usually by an immersion method, but other methods may also be employed.

[0032] Now, the present invention will be explained in further detail with reference to Examples and Comparative Examples. However, it should be understood that the present invention is by no means restricted to such specific Examples.

EXAMPLES 1 to 27 and COMPARATIVE EXAMPLES 1 to 8

[0033] A commercially available positive photoresist was coated in a thickness of 2 μm on a silicon wafer, followed by prebaking. Then, exposure by means of a mask pattern and development with tetramethylammonium hydroxide were carried out. Etching was carried out, and then plasma ashing treatment was carried out. This silicon wafer was immersed in a stripping solution as identified in Table 1 at 80°C for 30 minutes, then washed with water and dried. The surface was observed by a scanning electron microscope to examine stripping properties of the resist degenerated membrane and stripping properties of a titanium oxide.

[0034] Further, corrosiveness of a metal was evaluated from weight change and surface observation after test specimen of each metal (copper, aluminum) were immersed in a resist stripper as identified in Table 2 at 50°C for 30 minutes.

[0035] Here, each of stripping solutions in Examples was prepared by adding a peroxide to a quaternary ammonium salt aqueous solution at 30°C, removing excess water and then adding an amine and a water soluble organic solvent. In a case of hydrogen peroxide, a 35% aqueous hydrogen peroxide solution was used, and the aqueous hydrogen peroxide solution was added to a quaternary ammonium salt aqueous solution at 80°C. The compositions are shown in Tables 1 and 2, and the rest consists of water in each Example.

Resist stripping properties and titanium oxide stripping properties

[0036] Stripping properties of the resist degenerated membrane and stripping properties of the titanium oxide were evaluated on the basis of the following standards:

O: Good stripping properties
 Δ: Some remained
 X: Most remained

5 Corrosiveness of metal

[0037] Corrosiveness against copper and aluminum was evaluated on the basis of the following standards (no test could be conducted with respect to hydroxylamine, since it decomposed when contacted with copper):

10 O: No corrosion
 Δ: Some corrosion observed
 X: Severe corrosion observed

[0038] Here, the following abbreviations were used to simplify the description in Tables 1 and 2.

15

TMAH: Tetramethylammonium hydroxide
 TEAH: Tetraethylammonium hydroxide
 TPAH: Tetra-n-propylammonium hydroxide
 TMHEAH: Trimethyl-2-hydroxyethylammonium hydroxide
 20 TMAC: Tetramethylammonium carbonate
 TPAC: Tetra-n-propylammonium carbonate
 TMHEAC: Trimethyl-2-hydroxyethylammonium carbonate
 BTMAC: Benzyltrimethylammonium carbonate
 TMAA: Tetramethylammonium acetate

25

TMAAP: Tetramethylammonium peracetate
 TMAS: Tetramethylammonium salicylate
 TMAB: Tetramethylammonium benzoate
 TMAL: Tetramethylammonium lactate
 TPAP: Tetra-n-propylammonium propionate

30

BTMAA: Benzyltrimethylammonium adipate
 MEA: Monoethanolamine
 HA: Hydroxylamine

TETA: Triethylenetetramine

HPO: Hydrogen peroxide

35

APS: Ammonium persulfate

APB: Ammonium perborate

APC: Ammonium percarbonate

BPO: Benzoyl peroxide

TBHPO: Tertiary butyl hydroperoxide

40

NMP: N-methyl-2-pyrrolidone

DMSO: Dimethylsulfoxide

45

50

55

Table 1

	Composition (wt%)				Stripping properties	
	Quaternary ammonium salt	Peroxide	Others		Resist	Titanium oxide
Example 1	TMAH(16)	HPO(6)	-	-	O	O
Example 2	TMAH(14)	HPO(5)	TETA(11)	-	O	O
Example 3	TMAH(14)	HPO(5)	-	DMSO(11)	O	O
Example 4	TEAH(30)	HPO(15)	-	-	O	O
Example 5	TEAH(16)	HPO(10)	TETA(4)	DMSO(10)	O	O
Example 6	TPAH(7)	HPO(3)	-	-	Δ	O
Example 7	TMHEAH(20)	HPO(5)	-	-	O	O
Example 8	TMAH(10)	APS(5)	-	-	O	Δ
Example 9	TMAH(8)	APB(2)	-	-	O	Δ
Example 10	TEAH(12)	APC(3)	-	DMSO(5)	O	Δ
Example 11	TEAH(7)	BPO(5)	TETA(5)	-	O	Δ
Example 12	TPAH(15)	TBHP(5)	-	TETA(5)	O	Δ
Comparative Example 1	TMAH(16)	-	-	-	Δ	×
Comparative Example 2	-	HPO(6)	-	-	×	Δ
Comparative Example 3	-	APS(5)	-	-	×	×
Comparative Example 4	MEA(16)*	-	TETA(4)	DMSO(10)	Δ	×
Comparative Example 5	HA(16)*	-	TETA(4)	DMSO(10)	O	O

* Each of MEA and HA is an amine, not a quaternary ammonium salt.

Table 2

	Composition (wt%)			Stripping properties		Corrosiveness	
	Quaternary ammonium salt	Peroxide	Others	Resist	Titanium oxide	Al	Cu
Example 13	TMAC(16)	HPO(6)		O	O	O	O
Example 14	TPAC(16)	HPO(6)		O	O	O	O
Example 15	BTMAC(16)	HPO(6)		O	O	O	O
Example 16	TMAC(40)	HPO(15)		O	O	O	O
Example 17	TMAC(3)	HPO(1)		O	O	O	O
Example 18	TMAC(5)	HPO(3)	DMSO(10)	O	O	O	O
Example 19	TMHEAC(20)	HPO(5)	NMP(50)	O	O	O	O
Example 20	TMAA(16)	HPO(6)		O	O	O	O
Example 21	TMAS(10)	HPO(5)		O	O	O	O
Example 22	TMAB(5)	HPO(2)		O	O	O	O
Example 23	TMAL(16)	HPO(15)		O	O	O	O
Example 24	TPAP(16)	HPO(10)		O	O	O	O
Example 25	BTMAA(5)	HPO(3)	DMSO(10)	O	O	O	O
Example 26	TMAAP(20)	HPO(5)	NMP(50)	O	O	O	O
Example 27	TMAS(5), TMAH(5)	HPO(5)		O	O	O	O
Comparative Example 6	TMAH(16)	HPO(6)		O	O	X	Δ
Comparative Example 7	MEA(16) *	-		Δ	X	O	X
Comparative Example 8	HA(16) *	-		O	O	Δ	-

* Each of MEA and HA is an amine, not a quaternary ammonium salt.

EXAMPLES 28 to 34

[0039] A resist stripping solution employing a peroxyhydrate of a quaternary ammonium salt was examined in the same manner as in Examples 1 to 27. The compositions and results are shown in Table 3.

5 [0040] Production Example of peroxyhydrate of tetramethylammonium hydroxide is shown below, and peroxyhydrates of other quaternary ammonium salts were produced in the same manner.

PRODUCTION EXAMPLE

10 [0041] 590 g (0.97 mol) of a 15% tetramethylammonium hydroxide was heated to 80°C, and 150 g (1.54 mol) of a 35% aqueous hydrogen peroxide solution was dropwise added thereto. The mixture was heated until blowing due to decomposition of excess hydrogen peroxide disappeared, and then water was distilled off under reduced pressure to obtain peroxyhydrate of tetramethylammonium hydroxide.

[0042] IR of the peroxyhydrate of tetramethylammonium hydroxide (KBr tablet): 1489, 1404, 949 cm⁻¹

15 [0043] This peroxyhydrate of tetramethylammonium hydroxide was dissolved in water, and an amine and a water soluble organic solvent were added thereto to prepare a resist stripping solution.

[0044] Here, the following abbreviations were used to simplify the description.

TMAH-H: Peroxyhydrate of tetramethylammonium hydroxide

TEAH-H: Peroxyhydrate of tetraethylammonium hydroxide

20 TPAH-H: Peroxyhydrate of tetra-n-propylammonium hydroxide

TMHEAH-H: Peroxyhydrate of trimethyl-2-hydroxyethylammonium hydroxide

25

30

35

40

45

50

55

Table 3

Example	Composition (wt%)			Resist stripping properties	Titanium oxide stripping properties
28	TMAH-H(22)	Water (78)		○	○
29	TMAH-H(19)	Water (70)	TETA(11)	○	○
30	TMAH-H(19)	Water (70)		○	○
31	TEAH-H(45)	Water (55)	DMSO(11)	○	○
32	TEAH-H(26)	Water (60)		○	○
33	TPAH-H(10)	Water (90)	DMSO(10)	△	○
34	TMHEAH-H(25)	Water (75)		○	○

[0045] The resist stripper of the present invention contains no hydroxylamine which is unstable and is highly hazardous, and is useful as a resist stripper showing excellent resist stripping properties and titanium oxide stripping

properties.

[0046] The entire disclosures of Japanese Patent Application No. 2000-369625 filed on November 30, 2000, Japanese Patent Application No. 2000-399153 filed on December 27, 2000, Japanese Patent Application No. 2000-399154 filed on December 27, 2000, Japanese Patent Application No. 2001-070360 filed on March 13, 2001 and Japanese Patent Application No. 2001-123252 filed on April 20, 2001 including specifications, claims and summaries are incorporated herein by reference in their entireties.

Claims

1. A resist stripper which comprises a peroxide and a quaternary ammonium salt.
2. The resist stripper according to Claim 1, wherein the quaternary ammonium salt is at least one member selected from quaternary ammonium hydroxide, a quaternary ammonium carbonate, a quaternary ammonium carboxylate and a quaternary ammonium peroxy-carboxylate.
3. The resist stripper according to Claim 2, wherein the carboxylic acid in the quaternary ammonium carboxylate is an aromatic carboxylic acid.
4. The resist stripper according to Claim 2 or 3, wherein the carboxylic acid in the quaternary ammonium carboxylate is at least one member selected from benzoic acid, salicylic acid and phthalic acid.
5. The resist stripper according to any one of Claims 1 to 4, wherein the quaternary ammonium in the quaternary ammonium salt is at least one member selected from a tetraalkyl ammonium, a benzyltrialkyl ammonium and an alkyl-hydroxyalkyl ammonium.
6. The resist stripper according to any one of Claims 1 to 5, wherein the peroxide is at least one member selected from hydrogen peroxide, a persulfate, a perborate, a percarbonate, an organic peracid and an organic hydroperoxide.
7. The resist stripper according to any one of Claims 1 to 6, wherein the peroxide and the quaternary ammonium salt are a peroxyhydrate of the quaternary ammonium salt.
8. The resist stripper according to any one of Claims 1 to 7, which has at least one member selected from an amine, a water soluble organic solvent and water added to the peroxide and the quaternary ammonium salt.
9. The resist stripper according to any one of Claims 1 to 8, wherein the water soluble organic solvent is at least one member selected from a sulfoxide, a sulfone, an amide, a lactam, an imidazolidinone, a glycol and a glycol ether.
10. The resist stripper according to any one of Claims 1 to 9, for stripping of a titanium oxide.
11. The resist stripper according to any one of Claims 1 to 10, for stripping of a resist or a resist residue remaining after development of a photoresist and formation of a circuit.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 12 8335

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 99 60448 A (SKEE DAVID C ;MALLINCKRODT INC (US)) 25 November 1999 (1999-11-25) * examples 20,25-35 *	1,2,5,6,8	G03F7/42 H01L21/3213 C11D7/26 C11D7/32
X	EP 1 005 072 A (WACKER SILTRONIC) 31 May 2000 (2000-05-31) * claims 2,9 *	1,2,5,6,8	C11D3/39 C11D7/50 C11D11/00
X	DATABASE WPI Section Ch, Week 199527 Derwent Publications Ltd., London, GB; Class A60, AN 1995-204353 XP002192035 & JP 07 118885 A (MITSUBISHI GAS CHEM CO INC), 9 May 1995 (1995-05-09) * abstract *	1	
X	WO 95 04372 A (SEMITOOL INC ;JOLLEY MICHAEL K (US)) 9 February 1995 (1995-02-09) * example 1 *	1,2,5,6,8	
X	EP 0 608 545 A (MITSUBISHI GAS CHEMICAL CO) 3 August 1994 (1994-08-03) * examples 1,2 *	1-3	TECHNICAL FIELDS SEARCHED (Int.Cl.7) G03F H01L C11D
X	EP 0 597 100 A (OHMI TADAHIRO) 18 May 1994 (1994-05-18) * claims *	1,2,5,6,8	
X	US 6 030 491 A (VAARTSTRA BRIAN A) 29 February 2000 (2000-02-29) * example 2 *	1-3,5,6,8	
X	EP 1 001 012 A (PROCTER & GAMBLE) 17 May 2000 (2000-05-17) * paragraph '0075! *	1,5,8	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 4 March 2002	Examiner Heywood, C
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (Pst/Co1)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 12 8335

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 99 41345 A (AUBAY ERIC ; RHONE POULENC CHIMIE (FR); POPOFF CHRISTINE (US)) 19 August 1999 (1999-08-19) * table 1 *	1	
X	WO 99 02637 A (BETTIOL JEAN LUC PHILIPPE ; PROCTER & GAMBLE (US); THOEN CHRISTIAAN) 21 January 1999 (1999-01-21) * page 63 *	1	
X	WO 99 01530 A (PROCTER & GAMBLE) 14 January 1999 (1999-01-14) * page 32 *	1	
X	US 5 840 127 A (KAKIZAWA MASAHICO ET AL) 24 November 1998 (1998-11-24) * example 5 *	1	
X	DATABASE WPI Section Ch, Week 199630 Derwent Publications Ltd., London, GB; Class E16, AN 1996-293098 XP002192036 & JP 08 124888 A (MITSUBISHI GAS CHEM CO INC), 17 May 1996 (1996-05-17) * abstract *	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
Place of search THE HAGUE		Date of completion of the search 4 March 2002	Examiner Heywood, C
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/02 (p.04/01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 8335

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

04-03-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9960448	A	25-11-1999	AU 4189599 A	06-12-1999
			WO 9960448 A1	25-11-1999
			CN 1309785 T	22-08-2001
			EP 1105778 A1	13-06-2001
EP 1005072	A	31-05-2000	DE 19853486 A1	31-05-2000
			DE 59900712 D1	28-02-2002
			EP 1005072 A1	31-05-2000
			JP 3181900 B2	03-07-2001
			JP 2000164560 A	16-06-2000
			US 2001003680 A1	14-06-2001
JP 7118885	A	09-05-1995	NONE	
WO 9504372	A	09-02-1995	AU 7221294 A	28-02-1995
			WO 9504372 A1	09-02-1995
			US 5489557 A	06-02-1996
EP 0608545	A	03-08-1994	JP 6329602 A	29-11-1994
			JP 6192867 A	12-07-1994
			DE 69309885 D1	22-05-1997
			DE 69309885 T2	24-07-1997
			EP 0608545 A1	03-08-1994
			KR 242979 B1	01-02-2000
			US 5393386 A	28-02-1995
EP 0597100	A	18-05-1994	JP 3115647 B2	11-12-2000
			JP 5011458 A	22-01-1993
			EP 0597100 A1	18-05-1994
			WO 9301527 A1	21-01-1993
US 6030491	A	29-02-2000	US 6207630 B1	27-03-2001
EP 1001012	A	17-05-2000	EP 1001012 A1	17-05-2000
			AU 1911600 A	29-05-2000
			WO 0027981 A1	18-05-2000
WO 9941345	A	19-08-1999	AU 2284599 A	30-08-1999
			WO 9941345 A1	19-08-1999
WO 9902637	A	21-01-1999	WO 9902637 A1	21-01-1999
			AU 3659797 A	08-02-1999
			BR 9714761 A	25-07-2000
			EP 1012220 A1	28-06-2000
			JP 2001509537 T	24-07-2001
			US 6187740 B1	13-02-2001

EPO FORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 8335

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

04-03-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9901530	A	14-01-1999	AU 7784898 A	25-01-1999
			BR 9810531 A	29-08-2000
			CN 1268160 T	27-09-2000
			EP 0996701 A1	03-05-2000
			WO 9901530 A1	14-01-1999
			US 6075000 A	13-06-2000
			ZA 9805774 A	06-01-1999
US 5840127	A	24-11-1998	DE 69520296 D1	19-04-2001
			DE 69520296 T2	06-09-2001
			EP 0665582 A2	02-08-1995
			JP 7254581 A	03-10-1995
			US 5580846 A	03-12-1996
JP 8124888	A	17-05-1996	NONE	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82